

Artificial Leather.

Parameter (unit).	Value.	Standard/ Method.
Width [mm]	≥ 1401	
Average thickness [mm]	≤ 1.14	BS EN ISO 2589:2002
Softness [mm]	≥ 3.1	IUP 36
GSM [g/m ²]	480 ± 40	EL-LSTP-0005
Tensile Force MD * I [N/mm]	≥ 9.7	BS EN ISO 3376:2002 * I
Tensile Force CD * I [N/mm]	≥ 9.9	BS EN ISO 3376:2002 * I
Breaking elongation MD [%]	≥ 19.9	BS EN ISO 3376:2002
Breaking elongation CD [%]	≥ 28.7	BS EN ISO 3376:2002
Peel strength [N/cm]	≥ 11.8	EL-LSTP-0003 Dry
Taber Abrasion CS10 lkg	>approx. 20,000 cycles	BS EN ISO 5470-I:1999 Part I

